

# SFA 309MoL(P)

Stainless steel wires (FcaW)

## Description

SFA 309MoL(P) is flux cored wire and designed for Fillet & H-F(All-position) welding with CO<sub>2</sub> gas Shielding. It provides the excellent usability with stable arc, less spattering, good bead appearance, better slag removal, and less quantity of welding fume comparable to solid wire. It contains a reasonable quantity of Ferrite and crack-resistance, intergranular corrosion resistance, mechanical properties of weld metal is superior. Shield gas is 100%CO<sub>2</sub> or Ar+CO<sub>2</sub> gas. For 22%Cr-12%Ni-2%Mo Stainless Steel.

## Notes on usage

The optimum flow of CO<sub>2</sub> for Shielding is 20~25ℓ/min. Protect the weld with a screen to prevent blowholes caused by wind where the wind velocity is 2 m/sec and more. Keep the distance between tip & base metal at 15~25mm.

## Applications

SFA 309L(P) is suitable for welding of 22%Cr-12%Ni-2%Mo steel and heat resistant steel and dissimilar joint such as a stainless steel to carbon steel of low alloy steel. Under layer welding on claded side groove claded stainless steel or carbon steel where stainless steel weld metal is overlaid.

## Classification

AWS A5.22 E309LMoT0(1)-1/-4

KS D 3612 YF309MoLC

JIS Z3323 TS309LMo-FB0(1)

## Typical weld metal chemical composition (%) (Shielding Gas : 100%CO<sub>2</sub>)

	C	Mn	Si	P	S	Cr	Ni	MO	FN
SFA 309MoL	0.03	1.40	0.55	0.015	0.010	23.0	13.0	2.5	23
SFA 309MoL(P)	0.03	0.74	0.66	0.017	0.009	22.6	12.8	2.3	22

## All weld metal mechanical properties (typical) (Shielding Gas : 100%CO<sub>2</sub>)

	Yield Strength N/mm <sup>2</sup> (MPa)	Tensile Strength N/mm <sup>2</sup> (MPa)	EL (%)	IV (J)
				0°C
SFA 309MoL	560	680	33.0	32
SFA 309MoL(P)	535	695	34.0	30

## Size & recommended current range (DC+)

Dia. mm (in)	Current (A)	Voltage (V)	Welding Speed (cm /min)
1.2(0.045)	150~300	24~33	20~60
1.6(0.062)	200~400	24~33	20~60